

**Structural carbon steel with max. operating temperature  $\leq 80^{\circ}\text{C}$  in internal and fully dry and ventilated areas**

System no.	Surface preparation	Coating system	DFT $\mu\text{m}$
8A-1	Sa 2½	Penguard Universal	<u>150</u> <b>150</b>
8A-2	Sa 2½	Jotamastic 90 WG	<u>150</u> <b>150</b>
8B-1	Sa 2½	Barrier Plus Penguard Tie Coat 100	60 <u>25</u> <b>85</b>